



Hardness test	58 ±0.3	Shore A
Density	0.90 ±2%	g/cm ³
Tensile strength	3	MPa
Elongation at tear	> 550	%

- ** SBS rubber (styrol-butadiene-styrol-mass polymer)
- ** Adjusted so as to be physiologically safe
- ** Fulfils Toy Standard EN 71/3
- ** Sporadic contact with foodstuff is possible
- ** Free of halogens and heavy metals
- ** Supplementary UV stabilisation
- ** Odourless

- Processing: approx. 170°C – 190°C according to moulded part
- Impact pressure: approx. 10%
- Injection speed: fast

The mentioned values are average values, which may be modified through pigments or additives. For this reason, no guarantee can be granted for the mentioned material characteristics.